

Filed 05/01/2001

1 of 64

COMMERCIAL TESTING & ENGINEERING CO.

ISP0086

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306



SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

July 21, 1998

Saeid Kamalpour
FYI.

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

INLAND STEEL COMPANY
Research Laboratory
3001 East Columbus Drive
East Chicago, IN 46312
Attn: Chuck Froman

L. Froman

Sample identification by
CT&E Co.

Kind of sample
reported to us Furnace Coke

Sample ID: Shenago Furnace Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled July 1, 1998

P.O. No. 6-H-8802

Date received July 1, 1998

ADDED CSR/CRI 7/21/98

Analysis Report No. 71-70527

Page 1 of 3

	<u>As Received</u>	<u>Dry Basis</u>
% Moisture	2.09	xxxxxx
% Ash	8.64	8.82
CRI		29.7
CSR		56.0
Bulk Density, Lb/Cf		27.0
% Porosity		53.43
Apparent Specific Gravity		0.89
True Specific Gravity		1.911
Stability		61.8
Void Fraction		.5366*

* Note: Void Fraction performed in a 1 cubic foot box.

METHODS

Ash: ASTM D 3174; Bulk Density: ASTM D 4292; Porosity: Calculated Value; Apparent Specific Gravity: Modified ASTM D 5004; True Specific Gravity: ASTM D 167; Stability: ASTM D 3402
Void Fraction: Inland Steel in-house procedure

BEST AVAILABLE COPY

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Joseph B. Horwin
Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

July 21, 1998

INLAND STEEL COMPANY
Research Laboratory
3001 East Columbus Drive
East Chicago, IN 46312
Attn: Chuck Froman

Sample identification by
CT&E Co.

Kind of sample
reported to us Furnace Coke

Sample ID: Shenago Furnace Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled July 1, 1998

P.O. No. 6-H-8802

Date received July 1, 1998

ADDED CSR/CRI 7/21/98

Analysis Report No. 71-70527

Page 2 of 3

MINERAL ANALYSISIgnited Basis, % Weight


Silica, SiO ₂	50.00
Alumina, Al ₂ O ₃	27.92
Titania, TiO ₂	1.18
Iron oxide, Fe ₂ O ₃	7.21
Calcium oxide, CaO	2.02
Magnesium oxide, MgO	0.71
Potassium oxide, K ₂ O	1.60
Sodium oxide, Na ₂ O	0.55
Sulfur trioxide, SO ₃	1.11
Phosphorus pentoxide, P ₂ O ₅	0.31
Strontium oxide, SrO	0.10
Barium oxide, BaO	0.10
Manganese oxide, Mn ₃ O ₄	0.07
Undetermined	7.12
	100.00

METHOD

Phosphorus pentoxide: ASTM D 2795; Sulfur trioxide: ASTM D 5016; Barium & Strontium oxide: ASTM D 3682-ICP
Balance of oxides: ASTM D 3682

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Joseph B. Horner
Manager, South Holland Laboratory



OVER 40 BRANCH LABORATORIES STRATEGICALLY LOCATED IN PRINCIPAL COAL MINING AREAS, TIDEWATER AND GREAT LAKES PORTS, AND RIVER LOADING FACILITIES

-465/071/95

ginal Watermarked For Your Protection

TERMS AND CONDITIONS ON REVERSE

COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
 16130 VAN DRUNEN RD.
 SOUTH HOLLAND, IL 60473
 TEL: (708) 331-2900
 FAX: (708) 333-3060

July 21, 1998

INLAND STEEL COMPANY
 Research Laboratory
 3001 East Columbus Drive
 East Chicago, IN 46312
 Attn: Chuck Froman

Sample identification by
 CT&E Co.

Kind of sample
 reported to us Furnace Coke

Sample ID: Shenago Furnace Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled July 1, 1998

P.O. No. 6-H-8802

Date received July 1, 1998

ADDED CSR/CRI 7/21/98

Analysis Report No. 71-70527

Page 3 of 3

SIEVE ANALYSIS

<u>Passing</u>	<u>Retained on</u>	<u>% Weight</u>	<u>CUMULATIVE RESULTS</u>	
			<u>% Retained</u>	<u>% Passing</u>
-----	4" Sq	0.00	0.00	100.00
4" Sq	3" Sq	4.20	4.20	95.80
3" Sq	2" Sq	41.41	45.61	54.39
2" Sq	1 1/4" Sq	45.19	90.80	9.20
1 1/4" Sq	1" Sq	6.73	97.53	2.47
1" Sq	3/8" Sq	1.39	98.92	1.08
3/8" Sq	0	1.08	100.00	0.00

METHOD

Sieve Analysis: ASTM D 293

Respectfully submitted,
 COMMERCIAL TESTING & ENGINEERING CO.

Joseph B. Housh
 Manager, South Holland Laboratory *SM*



COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

August 31, 1998

INLAND STEEL COMPANY
Plant 2 Blast Furnaces (2-606)
3210 Watling Street
East Chicago, IN 46312
Attn: Chuck Froman

Sample identification by
CT&E Co.

Kind of sample
reported to us Furnace Coke

Sample ID: Shenango Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled August 7, 1998

P.O. No. 6-H-8802

Date received August 7, 1998

Analysis Report No. 71-73635

Page 1 of 4

CRI	21.1
CSR	69.9
Bulk Density, Lb/Cf	30.6
% Porosity	48.70
Apparent Specific Gravity	0.99
True Specific Gravity	1.93
Stability	62.8
Void Fraction	.5504

* Note: Void Fraction performed in a 1 cubic foot box.

METHODS

Bulk Density: ASTM D 4292; Porosity: Calculated Value; Apparent Specific Gravity: Modified ASTM D 5004; True Specific Gravity: ASTM D 167; Stability: ASTM D 3402
Void Fraction: Inland Steel in-house procedure

10/7/98

Bill,

FYI.

CAF

CO.



Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

August 31, 1998

INLAND STEEL COMPANY
Plant 2 Blast Furnaces (2-606)
3210 Watling Street
East Chicago, IN 46312
Attn: Chuck Froman

Sample identification by
CT&E Co.

Kind of sample
reported to us Furnace Coke

Sample ID: Shenango Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled August 7, 1998

P.O. No. 6-H-8802

Date received August 7, 1998

Analysis Report No. 71-73635

Page 2 of 4

MINERAL ANALYSISIgnited Basis, % Weight

Silica, SiO ₂	51.00
Alumina, Al ₂ O ₃	27.30
Titania, TiO ₂	1.15
Iron oxide, Fe ₂ O ₃	13.46
Calcium oxide, CaO	1.41
Magnesium oxide, MgO	0.72
Potassium oxide, K ₂ O	1.80
Sodium oxide, Na ₂ O	0.62
Sulfur trioxide, SO ₃	0.83
Phosphorus pentoxide, P ₂ O ₅	0.26
Strontium oxide, SrO	0.09
Barium oxide, BaO	0.08
Manganese oxide, Mn ₃ O ₄	0.07
Undetermined	1.21
	100.00

METHOD

Phosphorus pentoxide: ASTM D 2795; Sulfur trioxide: ASTM D 5016; Barium & Strontium oxide: ASTM D 3682-ICP
Balance of oxides: ASTM D 3682

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Manager, South Holland Laboratory



SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

August 31, 1998

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

INLAND STEEL COMPANY
Plant 2 Blast Furnaces (2-606)
3210 Watling Street
East Chicago, IN 46312
Attn: Chuck Froman
Mail Code 2606

Sample identification by
CT&E Co.

Kind of sample
reported to us Furnace Coke

Sample ID: Shenango Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled August 7, 1998

P.O. No. 6-H-8802

Date received August 7, 1998

Analysis Report No. 71-73635

Page 3 of 4

SIEVE ANALYSIS

<u>Passing</u>	<u>Retained on</u>	<u>% Weight</u>	<u>CUMULATIVE RESULTS</u>	
			<u>% Retained</u>	<u>% Passing</u>
-----	4" Sq	0.00	0.00	100.00
4" Sq	3" Sq	2.23	2.23	97.77
3" Sq	2" Sq	32.89	35.12	64.88
2" Sq	1 1/4" Sq	50.99	86.11	13.89
1 1/4" Sq	1" Sq	9.88	95.99	4.01
1" Sq	3/8" Sq	1.96	97.95	2.05
3/8" Sq	0	2.05	100.00	0.00

METHOD

Sieve Analysis: ASTM D 293

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.



Manager, South Holland Laboratory



SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

August 31, 1998

INLAND STEEL COMPANY
Plant 2 Blast Furnaces (2-606)
3210 Watling Street
East Chicago, IN 46312
Attn: Chuck Froman

Sample identification by
CT&E Co.

Kind of sample
reported to us Furnace Coke

Sample ID: Shenango Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled August 7, 1998

P.O. No. 6-H-8802

Date received August 7, 1998

Analysis Report No. 71-73635

Page 4 of 4

SHORT PROXIMATE ANALYSIS

	<u>As Received</u>	<u>Dry Basis</u>	
% Moisture	4.34	XXXXXX	
% Ash	8.84	9.24	
Btu/lb	12660	13234	MAF 14581
% Sulfur	0.70	0.73	

METHODS

Moisture: ASTM D 4931; Ash: ASTM D 4422; Btu/lb: ASTM D 3286; Sulfur: ASTM D 4239 (Method C)

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.



Manager, South Holland Laboratory

COMMERCIAL TESTING & ENGINEERING CO.

ISP0086

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
18130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

September 22, 1998

INLAND STEEL COMPANY
Research Laboratory
3001 East Columbus Drive
East Chicago, IN 46312
Attn: Pinakin Chaubal

Sample identification by
CT&E Co.

Kind of sample
reported to us Furnace Coke

Sample taken at Inland Steel Company

Sample ID: Indy Furnace Coke
No. 6 Stockhouse

Sample taken by CT&E Co.

Date sampled September 2, 1998

Date received September 2, 1998

P.O. No. 6-H-8802

Analysis Report No. 71-75649

Page 1 of 4

SMALL PROXIMATE ANALYSIS

	<u>As Received</u>	<u>Dry Basis</u>
% Moisture	2.75	XXXXXX
% Ash	7.78	8.00
% Volatile	0.51	0.52
% Fixed Carbon	<u>88.96</u>	<u>91.48</u>
	100.00	100.00
% Sulfur	0.50	0.51
CSR		57.8
CRI		32.1

METHODS

Moisture: ASTM D 3302; Ash: ASTM D 3174; Volatile: ASTM D 3175; Fixed Carbon: Calculated Value; ASTM D 3172
Sulfur: ASTM D 4239 (Method C); CSR/CRI ASTM D 5341

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
18130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 80473
TEL: (708) 331-2900
FAX: (708) 333-3060

September 22, 1998

INLAND STEEL COMPANY
Research Laboratory
3001 East Columbus Drive
East Chicago, IN 46312
Attn: Pinakin ChaubalSample identification by
CT&E Co.Kind of sample
reported to us Furnace Coke

Sample taken at Inland Steel Company

Sample ID: Indy Furnace Coke
No. 6 Stockhouse

Sample taken by CT&E Co.

Date sampled September 2, 1998

Date received September 2, 1998

P.O. No. 6-H-8802

Analysis Report No. 71-75649

Page 2 of 4

MINERAL ANALYSISIgnited Basis, % Weight

Silica, SiO ₂	50.74
Alumina, Al ₂ O ₃	29.42
Titania, TiO ₂	1.42
Iron oxide, Fe ₂ O ₃	13.12
Calcium oxide, CaO	0.76
Magnesium oxide, MgO	0.75
Potassium oxide, K ₂ O	1.75
Sodium oxide, Na ₂ O	0.75
Sulfur trioxide, SO ₃	0.15
Phosphorus pentoxide, P ₂ O ₅	0.18
Strontium oxide, SrO	0.11
Barium oxide, BaO	0.11
Manganese oxide, Mn ₃ O ₄	0.10
Undetermined	0.64
	100.00

METHODPhosphorus pentoxide: ASTM D 2795; Sulfur trioxide: ASTM D 5016; Barium & Strontium oxide: ASTM D 3682-ICP
Balance of oxides: ASTM D 3682Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Manager, South Holland Laboratory



OVER 40 BRANCH LABORATORIES STRATEGICALLY LOCATED IN PRINCIPAL COAL MINING AREAS, TIDEWATER AND GREAT LAKES PORTS, AND RIVER LOADING FACILITIES

171/95
Watermarked For Your Protection

TERMS AND CONDITIONS ON REVERSE

COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-8300 FAX: 708-953-9306

SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:

18130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 80473
TEL: (708) 331-2900
FAX: (708) 333-3060

September 22, 1998

INLAND STEEL COMPANY
Research Laboratory
3001 East Columbus Drive
East Chicago, IN 46312
Attn: Pinakin ChaubalSample identification by
CT&E Co.Kind of sample
reported to us Furnace Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled September 2, 1998

Date received September 2, 1998

Sample ID: Indy Furnace Coke
No. 6 Stockhouse

P.O. No. 6-H-8802

Analysis Report No. 71-75649

Page 3 of 4

SIEVE ANALYSIS

Passing	Retained on	% Weight	CUMULATIVE RESULTS	
			% Retained	% Passing
-----	4" Sq	0.00	0.00	100.00
4" Sq	3 1/2" Sq	0.00	0.00	100.00
3 1/2" Sq	3" Sq	1.14	1.14	98.86
3" Sq	2 1/2" Sq	6.00	7.14	92.86
2 1/2" Sq	2" Sq	18.12	25.26	74.74
2" Sq	1 1/2" Sq	41.69	66.95	33.05
1 1/2" Sq	1 1/4" Sq	20.15	87.10	12.90
1 1/4" Sq	1" Sq	9.12 _{30.96}	96.22	3.78
1" Sq	0	3.78	100.00	0.00

METHOD

Sieve Analysis: ASTM D 293

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Manager, South Holland Laboratory



Filed 05/01/2001

11 of 64

COMMERCIAL TESTING & ENGINEERING CO.

ISP0086

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9308

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3080

September 22, 1998

INLAND STEEL COMPANY
Research Laboratory
3001 East Columbus Drive
East Chicago, IN 46312
Attn: Pinakin Chaubal

Sample identification by
CT&E Co.

Kind of sample
reported to us Furnace Coke

Sample taken at Inland Steel Company

Sample ID: Indy Furnace Coke
No. 6 Stockhouse

Sample taken by CT&E Co.

Date sampled September 2, 1998

Date received September 2, 1998

P.O. No. 6-H-8802

Analysis Report No. 71-75649

Page 4 of 4

Bulk Density, Lb/Cf	31.3
Apparent Specific Gravity	0.958
True Specific Gravity	1.89
Porosity	49.31
Void Fraction	0.5019 *

Tumbler Test

Stability	62.8
Hardness	64.8

* NOTE: Void Fraction performed in a 1 cubic foot box.

METHODS

Bulk Density: ASTM D 4292; Porosity: Calculated Value; Apparent Specific Gravity, True Specific Gravity, & Porosity: ASTM D 167; Stability/Hardness: ASTM D3402
Void Fraction: Inland in-house procedure

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Manager, South Holland Laboratory





Appl. No. 09/846,829

Filed 05/01/1999

COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

EXHIBIT D

12 of 64

ISP0086

SINCE 1909

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
 16130 VAN DRUNEN RD.
 SOUTH HOLLAND, IL 60473
 TEL: (708) 331-2900
 FAX: (708) 333-3060

October 23, 1998

INLAND STEEL COMPANY
 Plant 2 Blast Furnaces (2-606)
 3210 Watling Street
 East Chicago, IN 46312
 Attn: Chuck Froman

Sample identification by
 CT&E Co.

Kind of sample
 reported to us Furnace Coke

Sample taken at Inland Steel Company

Sample ID: Mitsui Furnace Coke
 No. 6 Stockhouse

Sample taken by CT&E Co.

Date sampled September 30, 1998

Date received September 30, 1998

P.O. No. 6-H-8802

Analysis Report No. 71-77195

Page 1 of 4

SHORT PROXIMATE ANALYSIS

	<u>As Received</u>	<u>Dry Basis</u>	
% Moisture	5.63	XXXXX	
% Ash	10.02	10.62	
Btu/lb	12213	12942	MAF 14480
% Sulfur	0.57	0.60	

METHODS

Moisture: ASTM D 4931; Ash: ASTM D 4422; Btu/lb: ASTM D 3286; Sulfur: ASTM D 4239 (Method C)

Respectfully submitted,
 COMMERCIAL TESTING & ENGINEERING CO.

Manager, South Holland Laboratory





Appl. No. 89/846 828

Filed 05/01/2001

COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

EXHIBIT D

13 of 64

ISP0086

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 80473
TEL: (708) 331-2900
FAX: (708) 333-3060

October 23, 1998

INLAND STEEL COMPANY
Plant 2 Blast Furnaces (2-606)
3210 Watling Street
East Chicago, IN 46312
Attn: Chuck Froman

Sample identification by
CT&E Co.

Kind of sample
reported to us Furnace Coke

Sample taken at Inland Steel Company

Sample ID: Mitsui Furnace Coke
No. 6 Stockhouse

Sample taken by CT&E Co.

Date sampled September 30, 1998

Date received September 30, 1998

P.O. No. 6-H-8802

Analysis Report No. 71-77195

Page 2 of 4

CRI	22.75
CSR	66.15
Bulk Density, Lb/Cf	33.4
% Porosity	49.47
Apparent Specific Gravity	0.96
True Specific Gravity	1.90
Stability	62.5
Void Fraction	.5158

* Note: Void Fraction performed in a 1 cubic foot box.

METHODS

Bulk Density: ASTM D 4292; Porosity: Calculated Value; Apparent Specific Gravity: Modified ASTM D 5004; True Specific Gravity: ASTM D 167; Stability: ASTM D 3402
Void Fraction: Inland Steel in-house procedure

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Manager, South Holland Laboratory



SINCE 1928

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

October 23, 1998

INLAND STEEL COMPANY
Plant 2 Blast Furnaces (2-606)
3210 Watling Street
East Chicago, IN 46312
Attn: Chuck Froman

Sample identification by
CT&E Co.

Kind of sample
reported to us Furnace Coke

Sample ID: Mitsui Furnace Coke
No. 6 Stockhouse

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled September 30, 1998

Date received September 30, 1998

P.O. No. 6-H-8802

Analysis Report No. 71-77195

Page 3 of 4

MINERAL ANALYSISIgnited Basis, % Weight

Silica, SiO ₂	55.81
Alumina, Al ₂ O ₃	31.62
Titania, TiO ₂	1.47
Iron oxide, Fe ₂ O ₃	3.93
Calcium oxide, CaO	2.13
Magnesium oxide, MgO	0.75
Potassium oxide, K ₂ O	0.80
Sodium oxide, Na ₂ O	0.51
Sulfur trioxide, SO ₃	0.45
Phosphorus pentoxide, P ₂ O ₅	0.65
Strontium oxide, SrO	0.10
Barium oxide, BaO	0.20
Manganese oxide, Mn ₃ O ₄	0.07
Undetermined	1.51
	100.00

METHOD

Phosphorus pentoxide: ASTM D 2795; Sulfur trioxide: ASTM D 5016; Barium & Strontium oxide: ASTM D 3682-1CP
Balance of oxides: ASTM D 3682

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Manager, South Holland Laboratory



October 23, 1998

INLAND STEEL COMPANY
 Plant 2 Blast Furnaces (2-606)
 3210 Watling Street
 East Chicago, IN 46312
 Attn: Chuck Froman
 Mail Code 2606

PLEASE ADDRESS ALL CORRESPONDENCE TO:
 16130 VAN DRUNEN RD.
 SOUTH HOLLAND, IL 60473
 TEL: (708) 331-2900
 FAX: (708) 333-3080

Sample identification by
 CT&E Co.

Kind of sample
 reported to us Furnace Coke

Sample taken at Inland Steel Company

Sample ID: Mitsui Furnace Coke
 No. 6 Stockhouse

Sample taken by CT&E Co.

Date sampled September 30, 1998

Date received September 30, 1998

P.O. No. 6-H-8802

Analysis Report No. 71-77195

Page 4 of 4

SIEVE ANALYSIS

<u>Passing</u>	<u>Retained on</u>	<u>% Weight</u>	<u>CUMULATIVE RESULTS</u>	
			<u>% Retained</u>	<u>% Passing</u>
-----	4" Sq	0.34	0.34	99.66
4" Sq	3" Sq	2.83	3.17	96.83
3" Sq	2" Sq	29.31	32.48	67.52
2" Sq	1 1/4" Sq	56.97	89.45	10.55
1 1/4" Sq	1" Sq	7.06	96.51	3.49
1" Sq	3/8" Sq	1.03	97.54	2.46
3/8" Sq	0	2.46	100.00	0.00
		3.49		

METHOD

Sieve Analysis: ASTM D 293

Respectfully submitted,
 COMMERCIAL TESTING & ENGINEERING CO.

Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

ISP0086

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

November 3, 1998

INLAND STEEL COMPANY
3210 Watling Street
Mail Code 8232
East Chicago, IN 46312
Attn: Bill Ambry - M/C 8161

Sample identification by
Inland Steel Company

Kind of sample
reported to us Furnace Coke

Sample ID: Mitsui Furnace Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled October 21, 1998

Release No. xxx
P.O. No. 6-H-8802

Date received October 21, 1998

Analysis Report No. 71-78623

Page 1 of 1

Porosity	50.00
Apparent Specific Gravity	0.97
True Specific Gravity	1.94

METHODS

Porosity: Calculated Value; Apparent Specific Gravity
True Specific Gravity: ASTM D 167

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Joseph B. Fournier
Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

November 10, 1998

INDIANA HARBOR COKE COMPANY
3210 Watling St. Mail C. 2-990
East Chicago, IN 46312
Attn: Joan Etter

Sample identification by
CT&E Co.

Kind of sample
reported to us Metallurgical Furnace Coke

Sample ID: 103198-A

Sample taken at Indiana Harbor Coke Co.

Sample taken by Mechanical by CT&E Co.

Date sampled October 31, 1998

Date received October 31, 1998

Analysis Report No. 71-79183

Page 1 of 1

Apparent Specific Gravity	0.97
True Specific Gravity	1.93
Porosity	49.7

METHODS

ASG/TSG/Porosity: ASTM D 167

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Joseph B. Abusery
Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

Member of the SGS Group (Société Générale de Surveillance)

November 10, 1998

INDIANA HARBOR COKE COMPANY
3210 Watling St. Mail C. 2-990
East Chicago, IN 46312
Attn: Joan Etter

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

Sample identification by
CT&E Co.

Kind of sample
reported to us Metallurgical Furnace Coke

Sample taken at Indiana Harbor Coke Co.

Sample ID: 103098-A

Sample taken by Mechanical by CT&E Co.

Date sampled October 30, 1998

Date received October 30, 1998

Analysis Report No. 71-79151

Page 1 of 1

Apparent Specific Gravity 0.94
True Specific Gravity 1.91
Porosity 50.8

METHODS

ASG/TSG/Porosity: ASTM D 167

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Joseph B. Abuser
Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

ISP0086

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

Member of the SGS Group (Société Générale de Surveillance)

November 10, 1998

INDIANA HARBOR COKE COMPANY
3210 Watling St. Mail C. 2-990
East Chicago, IN 46312
Attn: Joan Etter

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

Sample identification by
CT&E Co.

Kind of sample
reported to us Metallurgical Furnace Coke

Sample taken at Indiana Harbor Coke Co.

Sample ID: 102998-A

Sample taken by Mechanical by CT&E Co.

Date sampled October 29, 1998

Date received October 29, 1998

Analysis Report No. 71-79166

Page 1 of 1

Apparent Specific Gravity	0.95
True Specific Gravity	1.93
Porosity	50.8

METHODS

ASG/TSG/Porosity: ASTM D 167

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Joseph B. Anderson
Manager, South Holland Laboratory





SINCE 1908

COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9308

Member of the SGS Group (Société Générale de Surveillance)

November 23, 1998

INDIANA HARBOR COKE COMPANY
3210 Watling St. Mail C. 2-990
East Chicago, IN 46312
Attn: Joan Etter

PLEASE ADDRESS ALL CORRESPONDENCE TO:
18130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3080

Sample identification by
CT&E Co.

Kind of sample
reported to us Metallurgical Furnace Coke

Sample taken at Indiana Harbor Coke Co.

Sample ID: 110298-A

Sample taken by Mechanical by CT&E Co.

Date sampled November 2, 1998

Date received November 2, 1998

Analysis Report No. 71-79321

Page 1 of 1

Apparent Specific Gravity	0.98
True Specific Gravity	1.94
Porosity	49.5

METHODS

ASG/TSG/Porosity: ASTM D 167

DISTRIBUTION

C. Ostenberg • Inland Steel Co.

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Joseph B. Finner
Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-8306

SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

November 23, 1998

INDIANA HARBOR COKE COMPANY
3210 Watling St. Mail C. 2-990
East Chicago, IN 46312
Attn: Joan Etter

PLEASE ADDRESS ALL CORRESPONDENCE TO:
18130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3080

Sample identification by
CT&E Co.

Kind of sample
reported to us Metallurgical Furnace Coke

Sample taken at Indiana Harbor Coke Co.

Sample taken by Mechanical by CT&E Co.

Date sampled November 1, 1998

Date received November 1, 1998

Sample ID: 110198-A

Analysis Report No. 71-79430

Page 1 of 1

Apparent Specific Gravity 0.97
True Specific Gravity 1.92
Porosity 49.6

METHODS


ASG/TSG/Porosity: ASTM D 167

DISTRIBUTION

C. Ostenberg - Inland Steel Co.

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Joseph B. Abuser
Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

January 21, 1999

INLAND STEEL COMPANY
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill Ambrey

Sample identification by
CT&E Co.

Kind of sample
reported to us Metallurgical Furnace Coke

Sample ID: Calculated Coke Composite
of IHCC Furnace Coke from
"A" Battery

Sample taken at Indiana Harbor Coke Co.

Sample taken by Mechanical by CT&E Co.

Date sampled October 29-31, 1998
November 1-2, 1998

Date received November 24, 1998

P.O. No. 6-J-8802

Analysis Report No. 71-80913-1

Page 1 of 3

SMALL PROXIMATE ANALYSIS

	<u>As Received</u>	<u>Dry Basis</u>
% Moisture	4.27	xxxxx
% Ash	8.39	8.76
% Volatile	0.41	0.43
% Fixed Carbon	<u>86.93</u>	<u>90.81</u>
	100.00	100.00
% Sulfur	0.61	0.64

METHODS

Moisture: ASTM D 3302; Ash: ASTM D 3174; Volatile: ASTM D 3175; Fixed Carbon: Calculated Value; ASTM D 3172
Sulfur: ASTM D 4239 (Method C)

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

January 21, 1999

INLAND STEEL COMPANY
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill Ambrey

Sample identification by
CT&E Co.

Kind of sample
reported to us Metallurgical Furnace Coke

Sample taken at Indiana Harbor Coke Co.

Sample taken by Mechanical by CT&E Co.

Date sampled October 29-31, 1998

November 1-2, 1998

Date received November 24, 1998

Sample ID: Calculated Coke Composite
of IHCC Furnace Coke from
"A" Battery

P.O. No. 6-J-8802

Analysis Report No. 71-80913-1

Page 2 of 3

Porosity 50.26

Apparent Specific Gravity 0.96

True Specific Gravity 1.93

Bulk Density lb/ft³ 29.5

METHODS

True & Apparent Specific Gravity: ASTM D 167; Porosity: Calculated Value

Density: ASTM D 291

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

January 21, 1999

INLAND STEEL COMPANY
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill AmbreySample identification by
CT&E Co.Kind of sample
reported to us Metallurgical Furnace Coke

Sample taken at Indiana Harbor Coke Co.

Sample ID: Calculated Coke Composite
of IHCC Furnace Coke from
"A" Battery

Sample taken by Mechanical by CT&E Co.

Date sampled October 29-31, 1998
November 1-2, 1998

Date received November 24, 1998

P.O. No. 6-J-8802

Analysis Report No. 71-80913-1

Page 3 of 3

SIEVE ANALYSIS

Passing	Retained on	% Weight	CUMULATIVE RESULTS	
			% Retained	% Passing
-----	4" Sq	0.00	0.00	100.00
4" Sq	3" Sq	10.01	10.01	89.99
3" Sq	2" Sq	41.22	51.23	48.77
2" Sq	1" Sq	45.42	96.65	3.35
1" Sq	0	3.35	100.00	0.00

METHOD

Sieve Analysis: ASTM D 293

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

January 21, 1999

INLAND STEEL COMPANY
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill AmbreySample identification by
Citizens G & C PersonnelKind of sample
reported to us Furnace CokeSample ID: Indy Coke
Drum #5

Sample taken at Citizens G & C, Indianapolis, IN

Sample taken by Citizens G & C Personnel

Date sampled -----

Date received November 24, 1998

P.O. No. 6-J-8802

Analysis Report No. 71-80592

Page 1 of 2


Porosity 49.46

Apparent Specific Gravity 0.93

True Specific Gravity 1.84

Bulk Density lb/ft³ 25.7METHODSTrue & Apparent Specific Gravity: ASTM D 167; Porosity: Calculated Value
Density: ASTM D 291Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

January 21, 1999

INLAND STEEL COMPANY
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill Ambrey

Sample identification by
Citizens G & C Personnel

Kind of sample
reported to us Furnace Coke

Sample ID: Indy Coke
Drum #5

Sample taken at Citizens G & C, Indianapolis, IN

Sample taken by Citizens G & C Personnel

Date sampled. -----

Date received November 24, 1998

P.O. No.6-J-8802

Analysis Report No. 71-80592

Page 2 of 2

SIEVE ANALYSIS

Passing	Retained on	% Weight	CUMULATIVE RESULTS	
			% Retained	% Passing
-----	4" Sq	0.00	0.00	100.00
4" Sq	3" Sq	24.97	24.97	75.03
3" Sq	2" Sq	55.80	80.77	19.23
2" Sq	1" Sq	18.23	99.00	1.00
1" Sq	0	1.00	100.00	0.00

METHOD

Sieve Analysis: ASTM D 293

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

January 21, 1999

INLAND STEEL COMPANY
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill Ambrey

Sample identification by
Citizens G & C Personnel

Kind of sample
reported to us Furnace Coke

Sample ID: Indy Coke
Drum #4

Sample taken at Citizens G & C, Indianapolis, IN

Sample taken by Citizens G & C Personnel

Date sampled -----

Date received November 24, 1998

P.O. No. 6-J-8802

Analysis Report No. 71-80591

Page 1 of 2

Porosity 49.46

Apparent Specific Gravity 0.94

True Specific Gravity 1.86

Bulk Density lb/ft³ 25.7

METHODS

True & Apparent Specific Gravity: ASTM D 167; Porosity: Calculated Value
Density: ASTM D 291

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Manager, South Holland Laboratory



OVER 40 BRANCH LABORATORIES STRATEGICALLY LOCATED IN PRINCIPAL COAL MINING AREAS, TIDEWATER AND GREAT LAKES PORTS, AND RIVER LOADING FACILITIES

465/071/95

Final Watermarked For Your Protection

TERMS AND CONDITIONS ON REVERSE

COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

January 21, 1999

INLAND STEEL COMPANY
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill Ambrey

Sample identification by
Citizens G & C Personnel

Kind of sample
reported to us Furnace Coke

Sample ID: Indy Coke
 Drum #4

Sample taken at Citizens G & C, Indianapolis, IN

Sample taken by Citizens G & C Personnel

Date sampled -----

Date received November 24, 1998

P.O. No. 6-J-8802

Analysis Report No. 71-80591

Page 2 of 2

SIEVE ANALYSIS

<u>Passing</u>	<u>Retained on</u>	<u>% Weight</u>	<u>CUMULATIVE RESULTS</u>	
			<u>% Retained</u>	<u>% Passing</u>
-----	4" Sq	0.00	0.00	100.00
4" Sq	3" Sq	9.87	9.87	90.13
3" Sq	2" Sq	45.57	55.44	44.56
2" Sq	1" Sq	41.90	97.34	2.66
1" Sq	0	2.66	100.00	0.00

METHOD

Sieve Analysis: ASTM D 293

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

[Signature]
(Manager, South Holland Laboratory)



COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

January 21, 1999

INLAND STEEL COMPANY
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill Ambrey

Sample identification by
Citizens G & C Personnel

Kind of sample
reported to us Furnace Coke

Sample ID: Indy Coke
 Drum #3

Sample taken at Citizens G & C, Indianapolis, IN

Sample taken by Citizens G & C Personnel

Date sampled -----

Date received November 24, 1998

P.O. No. 6-J-8802

Analysis Report No. 71-80590

Page 1 of 2

Porosity 47.51

Apparent Specific Gravity 0.95

True Specific Gravity 1.81

Bulk Density lb/ft³ 27.1

METHODS

True & Apparent Specific Gravity: ASTM D 167; Porosity: Calculated Value

Density: ASTM D 291

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

ISP0086

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:

16130 VAN DRUNEN RD.

SOUTH HOLLAND, IL 60473

TEL: (708) 331-2900

FAX: (708) 333-3060

January 21, 1999

INLAND STEEL COMPANY
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill Ambrey

Sample identification by
Citizens G & C Personnel

Kind of sample
reported to us Furnace Coke

Sample ID: Indy Coke
 Drum #3

Sample taken at Citizens G & C, Indianapolis, IN

Sample taken by Citizens G & C Personnel

Date sampled -----

Date received November 24, 1998.

P.O. No.6-J-8802

Analysis Report No. 71-80590

Page 2 of 2

SIEVE ANALYSIS

<u>Passing</u>	<u>Retained on</u>	<u>% Weight</u>	<u>CUMULATIVE RESULTS</u>	
			<u>% Retained</u>	<u>% Passing</u>
-----	4" Sq	0.00	0.00	100.00
4" Sq	3" Sq	10.48	10.48	89.52
3" Sq	2" Sq	34.64	45.12	54.88
2" Sq	1" Sq	51.43	96.55	3.45
1" Sq	0	3.45	100.00	0.00

METHOD

Sieve Analysis: ASTM D 293

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

[Signature]
Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

January 21, 1999

INLAND STEEL COMPANY
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill Ambrey

Sample identification by
Citizens G & C Personnel

Kind of sample
reported to us Furnace Coke

Sample ID: Indy Coke
 Drum #2

Sample taken at Citizens G & C, Indianapolis, IN

Sample taken by Citizens G & C Personnel

Date sampled -----

Date received November 24, 1998

P.O. No. 6-J-8802

Analysis Report No. 71-80589

Page 1 of 2

Porosity	49.73
Apparent Specific Gravity	0.93
True Specific Gravity	1.85
Bulk Density lb/ft ³	27.4

METHODS

True & Apparent Specific Gravity: ASTM D 167; Porosity: Calculated Value
Density: ASTM D 291

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Joseph A. H.
Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

January 21, 1999

INLAND STEEL COMPANY
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill Ambrey

Sample identification by
Citizens G & C Personnel

Kind of sample
reported to us Furnace Coke

Sample ID: Indy Coke
Drum #2

Sample taken at Citizens G & C, Indianapolis, IN

Sample taken by Citizens G & C Personnel

Date sampled -----

Date received November 24, 1998

P.O. No. 6-J-8802

Analysis Report No. 71-80589

Page 2 of 2

SIEVE ANALYSIS

<u>Passing</u>	<u>Retained on</u>	<u>% Weight</u>	<u>CUMULATIVE RESULTS</u>	
			<u>% Retained</u>	<u>% Passing</u>
-----	4" Sq	0.00	0.00	100.00
4" Sq	3" Sq	12.48	12.48	87.52
3" Sq	2" Sq	52.97	65.45	34.55
2" Sq	1" Sq	32.41	97.86	2.14
1" Sq	0	2.14	100.00	0.00

METHOD

Sieve Analysis: ASTM D 293

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

January 21, 1999

INLAND STEEL COMPANY
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill Ambrey

Sample identification by
Citizens G & C Personnel

Kind of sample
reported to us Furnace Coke

Sample ID: Indy Coke
 Drum #1

Sample taken at Citizens G & C, Indianapolis, IN

Sample taken by Citizens G & C Personnel

Date sampled -----

Date received November 24, 1998

P.O. No. 6-J-8802

Analysis Report No. 71-80588

Page 1 of 2

Porosity 48.07

Apparent Specific Gravity 0.94

True Specific Gravity 1.81

Bulk Density lb/ft³ 27.5

METHODS

True & Apparent Specific Gravity: ASTM D 167; Porosity: Calculated Value
Density: ASTM D 291

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

ISP0086

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

January 21, 1999

INLAND STEEL COMPANY
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill Ambrey

Sample identification by
Citizens G & C Personnel

Kind of sample
reported to us Furnace Coke

Sample ID: Indy Coke
Drum #1

Sample taken at Citizens G & C, Indianapolis, IN

Sample taken by Citizens G & C Personnel

Date sampled -----

Date received November 24, 1998

P.O. No. 6-J-8802

Analysis Report No. 71-80588

Page 2 of 2

SIEVE ANALYSIS


Passing	Retained on	% Weight	CUMULATIVE RESULTS	
			% Retained	% Passing
-----	4" Sq	0.00	0.00	100.00
4" Sq	3" Sq	12.82	12.82	87.18
3" Sq	2" Sq	36.51	49.33	50.67
2" Sq	1" Sq	46.40	95.73	4.27
1" Sq	0	4.27	100.00	0.00

METHOD

Sieve Analysis: ASTM D 293

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

[Signature]
Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

February 10, 1999

INLAND STEEL COMPANY
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill Ambrey

Sample identification by
CT&E Co.

Kind of sample
reported to us Furnace Coke

Sample ID: Mitsui Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled February 1, 1999

Date received February 2, 1999

P.O. No. 6-J-8802

Analysis Report No. 71-84902

Page 1 of 2


Porosity	51.55
Apparent Specific Gravity	0.94
True Specific Gravity	1.95
Bulk Density lb/ft ³	35.1

METHODS

True & Apparent Specific Gravity: ASTM D 167; Porosity: Calculated Value; Density: ASTM D 291

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Joseph B. Frouser
Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

ISP0086

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
 16130 VAN DRUNEN RD.
 SOUTH HOLLAND, IL 60473
 TEL: (708) 331-2900
 FAX: (708) 333-3060

February 10, 1999

INLAND STEEL COMPANY
 3210 Watling Street
 Mail Code 8161
 East Chicago, IN 46312
 Attn: Bill Ambrey

Sample identification by
 CT&E Co.

Kind of sample
 reported to us Furnace Coke

Sample ID: Mitsui Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled February 1, 1999

Date received February 2, 1999

P.O. No. 6-J-8802

Analysis Report No. 71-84902

Page 2 of 2

SIEVE ANALYSIS

<u>Passing</u>	<u>Retained on</u>	<u>% Weight</u>	<u>CUMULATIVE RESULTS</u>	
			<u>% Retained</u>	<u>% Passing</u>
-----	4" Sq	0.00	0.00	100.00
4" Sq	3" Sq	1.22	1.22	98.78
3" Sq	2" Sq	20.54	21.76	78.24
2" Sq	1" Sq	67.82	89.58	10.42
1" Sq	0	10.42	100.00	0.00

METHOD

Sieve Analysis: ASTM D 4749

Respectfully submitted,
 COMMERCIAL TESTING & ENGINEERING CO.

Joseph B. Ambrey
 Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

ISP0086

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306



SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

February 10, 1999

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

INLAND STEEL COMPANY
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill Ambrey

Sample identification by
CT&E Co.

Kind of sample
reported to us Furnace Coke

Sample ID: Mitsui Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled January 29, 1999

Date received January 29, 1999

P.O. No. 6-J-8802

Analysis Report No. 71-84771

Page 1 of 2


Porosity	48.26
Apparent Specific Gravity	0.98
True Specific Gravity	1.89
Bulk Density lb/ft ³	34.9

METHODS

True & Apparent Specific Gravity: ASTM D 167; Porosity: Calculated Value; Density: ASTM D 291

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Joseph B. Ambrey
Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

ISP0086

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

February 10, 1999

INLAND STEEL COMPANY
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill Ambrey

Sample identification by
CT&E Co.

Kind of sample
reported to us Furnace Coke

Sample ID: Mitsui Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled January 29, 1999

Date received January 29, 1999

P.O. No. 6-J-8802

Analysis Report No. 71-84771

Page 2 of 2

SIEVE ANALYSIS

<u>Passing</u>	<u>Retained on</u>	<u>% Weight</u>	<u>CUMULATIVE RESULTS</u>	
			<u>% Retained</u>	<u>% Passing</u>
-----	4" Sq	0.65	0.65	99.35
4" Sq	3" Sq	2.59	3.24	96.76
3" Sq	2" Sq	33.62	36.86	63.14
2" Sq	1" Sq	57.75	94.61	5.39
1" Sq	0	5.39	100.00	0.00

METHOD

Sieve Analysis: ASTM D 4749

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Joseph B. Ambrey
Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

ISP0086

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

February 10, 1999

INLAND STEEL COMPANY
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill Ambrey

Sample identification by
CT&E Co.

Kind of sample
reported to us Furnace Coke

Sample ID: Shenango Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled February 1, 1999

Date received February 2, 1999

P.O. No. 6-J-8802

Analysis Report No. 71-84901

Page 1 of 2

Porosity	52.56
Apparent Specific Gravity	0.90
True Specific Gravity	1.90
Bulk Density lb/ft ³	33.1

METHODS

True & Apparent Specific Gravity: ASTM D 167; Porosity: Calculated Value; Density: ASTM D 291

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Joseph B. Ambrey
Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

February 10, 1999

INLAND STEEL COMPANY
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill Ambrey

Sample identification by
CT&E Co.

Kind of sample
reported to us Furnace Coke

Sample ID: Shenango Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled February 1, 1999

Date received February 2, 1999

P.O. No. 6-J-8802

Analysis Report No. 71-84901

Page 2 of 2

SIEVE ANALYSIS

<u>Passing</u>	<u>Retained on</u>	<u>% Weight</u>	<u>CUMULATIVE RESULTS</u>	
			<u>% Retained</u>	<u>% Passing</u>
-----	4" Sq	0.00	0.00	100.00
4" Sq	3" Sq	1.44	1.44	98.56
3" Sq	2" Sq	21.85	23.29	76.71
2" Sq	1" Sq	61.86	85.15	14.85
1" Sq	0	14.85	100.00	0.00

METHOD

Sieve Analysis: ASTM D 4749

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Joseph B. Hruska
Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

February 10, 1999

INLAND STEEL COMPANY
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill Ambrey

Sample identification by
CT&E Co.

Kind of sample
reported to us Furnace Coke

Sample ID: Shenango Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled January 29, 1999

Date received January 29, 1999

P.O. No. 6-J-8802

Analysis Report No. 71-84770

Page 1 of 2


Porosity	55.32
Apparent Specific Gravity	0.84
True Specific Gravity	1.88
Bulk Density lb/ft ³	31.2

METHODS

True & Apparent Specific Gravity: ASTM D 167; Porosity: Calculated Value; Density: ASTM D 291

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Joseph B. Frouser
Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

ISP0086

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

February 10, 1999

PLEASE ADDRESS ALL CORRESPONDENCE TO:
 16130 VAN DRUNEN RD.
 SOUTH HOLLAND, IL 60473
 TEL: (708) 331-2900
 FAX: (708) 333-3060

INLAND STEEL COMPANY
 3210 Watling Street
 Mail Code 8161
 East Chicago, IN 46312
 Attn: Bill Ambrey

Sample identification by
 CT&E Co.

Kind of sample
 reported to us Furnace Coke

Sample ID: Shenango Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled January 29, 1999

Date received January 29, 1999

P.O. No. 6-J-8802

Analysis Report No. 71-84770

Page 2 of 2

SIEVE ANALYSIS


<u>Passing</u>	<u>Retained on</u>	<u>% Weight</u>	<u>CUMULATIVE RESULTS</u>	
			<u>% Retained</u>	<u>% Passing</u>
-----	4" Sq	0.00	0.00	100.00
4" Sq	3" Sq	4.82	4.82	95.18
3" Sq	2" Sq	27.89	32.71	67.29
2" Sq	1" Sq	55.96	88.67	11.33
1" Sq	0	11.33	100.00	0.00

METHOD

Sieve Analysis: ASTM D 4749

Respectfully submitted,
 COMMERCIAL TESTING & ENGINEERING CO.

Joseph B. Ambrey
 Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

ISP0086

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

February 18, 1999

INLAND STEEL COMPANY
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill Ambrey

Sample identification by
CT&E Co.

Kind of sample
reported to us Furnace Coke

Sample ID: Usx Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled February 2, 1999

Release No. XXX
P.O. No. 6-J-8802

Date received February 3, 1999

Analysis Report No. 71-84979

Page 1 of 2


Porosity	51.61
Apparent Specific Gravity	0.90
True Specific Gravity	1.86
Bulk Density lb/ft ³	31.7

METHODS

True & Apparent Specific Gravity: ASTM D 167; Porosity: Calculated Value; Density: ASTM D 291

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Joseph B. Ambrey
Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

ISP0086

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
 16130 VAN DRUNEN RD.
 SOUTH HOLLAND, IL 60473
 TEL: (708) 331-2900
 FAX: (708) 333-3060

February 18, 1999

INLAND STEEL COMPANY
 3210 Watling Street
 Mail Code 8161
 East Chicago, IN 46312
 Attn: Bill Ambrey

Sample identification by
 CT&E Co.

Kind of sample
 reported to us Furnace Coke

Sample ID: Usx Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled February 2, 1999

Release No. XXX
 P.O. No. 6-J-8802

Date received February 3, 1999

Analysis Report No. 71-84979

Page 2 of 2

SIEVE ANALYSIS

<u>Passing</u>	<u>Retained on</u>	<u>% Weight</u>	<u>CUMULATIVE RESULTS</u>	
			<u>% Retained</u>	<u>%Passing</u>
-----	4" Sq	0.00	0.00	100.00
4" Sq	3" Sq	2.83	2.83	97.17
3" Sq	2" Sq	35.10	37.93	62.07
2" Sq	1" Sq	55.68	93.61	6.39
1" Sq	0	6.39	100.00	0.00

METHOD

Sieve Analysis: ASTM D 4749

Respectfully submitted,
 COMMERCIAL TESTING & ENGINEERING CO.

Joseph B. Fouser
 Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

February 18, 1999

INLAND STEEL COMPANY
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill Ambrey

Sample identification by
CT&E Co.

Kind of sample
reported to us Furnace Coke

Sample ID: Mitsui Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled February 3, 1999

Release No. XXX
P.O. No. 6-J-8802

Date received February 3, 1999

Analysis Report No. 71-85066

Page 1 of 2

Porosity	47.28
Apparent Specific Gravity	0.97
True Specific Gravity	1.84
Bulk Density lb/ft ³	33.6

METHODS

True & Apparent Specific Gravity: ASTM D 167; Porosity: Calculated Value; Density: ASTM D 291

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Joseph B. Ambrey
Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
 16130 VAN DRUNEN RD.
 SOUTH HOLLAND, IL 60473
 TEL: (708) 331-2900
 FAX: (708) 333-3060

February 18, 1999

INLAND STEEL COMPANY
 3210 Watling Street
 Mail Code 8161
 East Chicago, IN 46312
 Attn: Bill Ambrey

Sample identification by
 CT&E Co.

Kind of sample
 reported to us Furnace Coke

Sample ID: Mitsui Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled February 3, 1999

Release No. XXX
 P.O. No. 6-J-8802

Date received February 3, 1999

Analysis Report No. 71-85066

Page 2 of 2

SIEVE ANALYSIS

<u>Passing</u>	<u>Retained on</u>	<u>% Weight</u>	<u>CUMULATIVE RESULTS</u>	
			<u>% Retained</u>	<u>% Passing</u>
-----	4" Sq	0.00	0.00	100.00
4" Sq	3" Sq	3.80	3.80	96.20
3" Sq	2" Sq	28.29	32.09	67.91
2" Sq	1" Sq	62.80	94.89	5.11
1" Sq	0	5.11	100.00	0.00

METHOD

Sieve Analysis: ASTM D 4749

Respectfully submitted,
 COMMERCIAL TESTING & ENGINEERING CO.

Joseph B. Fouser
 Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:

16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

February 18, 1999

INLAND STEEL COMPANY
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill AmbreySample identification by
CT&E Co.Kind of sample
reported to us Furnace Coke

Sample ID: USX Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled February 3, 1999

Release No. XXX
P.O. No. 6-J-8802

Date received February 3, 1999


Analysis Report No. 71-85067

Page 1 of 2

Porosity	51.10
Apparent Specific Gravity	0.89
True Specific Gravity	1.82
Bulk Density lb/ft ³	32.6

METHODS

True & Apparent Specific Gravity: ASTM D 167; Porosity: Calculated Value; Density: ASTM D 291

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.
Manager, South Holland Laboratory

COMMERCIAL TESTING & ENGINEERING CO.

ISP0086

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:

16130 VAN DRUNEN RD.

SOUTH HOLLAND, IL 60473

TEL: (708) 331-2900

FAX: (708) 333-3060

February 18, 1999

INLAND STEEL COMPANY
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill Ambrey

Sample identification by
CT&E Co.

Kind of sample
reported to us Furnace Coke

Sample ID: USX Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled February 3, 1999

Release No. XXX

Date received February 3, 1999

P.O. No. 6-J-8802

Analysis Report No. 71-85067

Page 2 of 2

SIEVE ANALYSIS


<u>Passing</u>	<u>Retained on</u>	<u>% Weight</u>	<u>CUMULATIVE RESULTS</u>	
			<u>% Retained</u>	<u>% Passing</u>
-----	4" Sq	0.00	0.00	100.00
4" Sq	3" Sq	0.60	0.60	99.40
3" Sq	2" Sq	22.62	23.22	76.78
2" Sq	1" Sq	58.49	81.71	18.29
1" Sq	0	18.29	100.00	0.00

METHOD

Sieve Analysis: ASTM D 4749

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Joseph B. Fouser
Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

ISP0086

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

February 18, 1999

INLAND STEEL COMPANY
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill Ambrey

Sample identification by
CT&E Co.

Kind of sample
reported to us Furnace Coke

Sample ID: Mitsui Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled February 2, 1999

Release No. XXX
P.O. No. 6-J-8802

Date received February 3, 1999

Analysis Report No. 71-84978

Page 1 of 2

Porosity	47.28
Apparent Specific Gravity	0.97
True Specific Gravity	1.84
Bulk Density lb/ft ³	38.3

METHODS

True & Apparent Specific Gravity: ASTM D 167; Porosity: Calculated Value; Density: ASTM D 291

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Joseph B. Ambrey
Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
 16130 VAN DRUNEN RD.
 SOUTH HOLLAND, IL 60473
 TEL: (708) 331-2900
 FAX: (708) 333-3060

February 18, 1999

INLAND STEEL COMPANY
 3210 Watling Street
 Mail Code 8161
 East Chicago, IN 46312
 Attn: Bill Ambrey

Sample identification by
 CT&E Co.

Kind of sample
 reported to us Furnace Coke

Sample ID: Mitsui Coke

Sample taken at Inland Steel Company.

Sample taken by CT&E Co.

Date sampled February 2, 1999

Release No. XXX

Date received February 3, 1999

P.O. No. 6-J-8802

Analysis Report No. 71-84978

Page 2 of 2

SIEVE ANALYSIS

<u>Passing</u>	<u>Retained on</u>	<u>% Weight</u>	<u>CUMULATIVE RESULTS</u>	
			<u>% Retained</u>	<u>% Passing</u>
-----	4" Sq	0.38	0.38	99.62
4" Sq	3" Sq	5.91	6.29	93.71
3" Sq	2" Sq	25.89	32.18	67.82
2" Sq	1" Sq	44.19	76.37	23.63
1" Sq	0	23.63	100.00	0.00

METHOD

Sieve Analysis: ASTM D 4749

Respectfully submitted,
 COMMERCIAL TESTING & ENGINEERING CO.

Joseph B. Houser
 Manager, South Holland Laboratory



OVER 40 BRANCH LABORATORIES STRATEGICALLY LOCATED IN PRINCIPAL COAL MINING AREAS, TIDEWATER AND GREAT LAKES PORTS, AND RIVER LOADING FACILITIES

465/071/95

Final Watermarked For Your Protection

TERMS AND CONDITIONS ON REVERSE

COMMERCIAL TESTING & ENGINEERING CO.

ISP0086

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306



Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

February 18, 1999

INLAND STEEL COMPANY
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill Ambrey

Sample identification by
CT&E Co.

Kind of sample
reported to us Furnace Coke

Sample ID: Shenango Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled February 3, 1999

Release No. XXX
P.O. No. 6-J-8802

Date received February 3, 1999

Analysis Report No. 71-85065

Page 1 of 2

Porosity	53.55
Apparent Specific Gravity	0.85
True Specific Gravity	1.83
Bulk Density lb/ft ³	33.5

METHODS

True & Apparent Specific Gravity: ASTM D 167; Porosity: Calculated Value; Density: ASTM D 291

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Joseph B. Fouser
Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

ISP0086

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

February 18, 1999

INLAND STEEL COMPANY
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill Ambrey

Sample identification by
CT&E Co.

Kind of sample
reported to us Furnace Coke

Sample ID: Shenango Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled February 3, 1999

Release No. XXX
P.O. No. 6-J-8802

Date received February 3, 1999

Analysis Report No. 71-85065

Page 2 of 2

SIEVE ANALYSIS


<u>Passing</u>	<u>Retained on</u>	<u>% Weight</u>	<u>CUMULATIVE RESULTS</u>	
			<u>% Retained</u>	<u>% Passing</u>
-----	4" Sq	0.00	0.00	100.00
4" Sq	3" Sq	3.06	3.06	96.94
3" Sq	2" Sq	26.83	29.89	70.11
2" Sq	1" Sq	45.30	75.19	24.81
1" Sq	0	24.81	100.00	0.00

METHOD

Sieve Analysis: ASTM D 4749

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Joseph B. Ambrey
Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

ISP0086

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306



Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

February 18, 1999

INLAND STEEL COMPANY
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill Ambrey

Sample identification by
CT&E Co.

Kind of sample
reported to us Furnace Coke

Sample ID: Shenago Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled February 2, 1999

Release No. XXX
P.O. No. 6-J-8802

Date received February 3, 1999

Analysis Report No. 71-84977

Page 1 of 2

Porosity	51.91
Apparent Specific Gravity	0.88
True Specific Gravity	1.83
Bulk Density lb/ft ³	30.1

METHODS

True & Apparent Specific Gravity: ASTM D 167; Porosity: Calculated Value; Density: ASTM D 291

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Joseph B. Ambrey
Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

February 18, 1999

INLAND STEEL COMPANY
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill Ambrey

Sample identification by
CT&E Co.

Kind of sample
reported to us Furnace Coke

Sample ID: Shenago Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled February 2, 1999

Release No. XXX
P.O. No. 6-J-8802

Date received February 3, 1999

Analysis Report No. 71-84977

Page 2 of 2

SIEVE ANALYSIS

<u>Passing</u>	<u>Retained on</u>	<u>% Weight</u>	<u>CUMULATIVE RESULTS</u>	
			<u>% Retained</u>	<u>%Passing</u>
-----	4" Sq	0.00	0.00	100.00
4" Sq	3" Sq	2.01	2.01	97.99
3" Sq	2" Sq	29.40	31.41	68.59
2" Sq	1" Sq	61.59	93.00	7.00
1" Sq	0	7.00	100.00	0.00

METHOD

Sieve Analysis: ASTM D 4749

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Joseph B. Ambrey
Manager, South Holland Laboratory



OVER 40 BRANCH LABORATORIES STRATEGICALLY LOCATED IN PRINCIPAL COAL MINING AREAS, TIDEWATER AND GREAT LAKES PORTS, AND RIVER LOADING FACILITIES

65/071/95
inal Watermarked For Your Protection

TERMS AND CONDITIONS ON REVERSE

COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:

16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

February 19, 1999

INLAND STEEL COMPANY
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill AmbreySample identification by
CT&E Co.Kind of sample
reported to us Furnace Coke

Sample ID: Mitsui Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled February 5, 1999

Release No. XXX


Date received February 5, 1999

P.O. No. 6-J-8802

Analysis Report No. 71-85160

Page 1 of 2

Porosity	51.81
Apparent Specific Gravity	0.93
True Specific Gravity	1.83
Bulk Density lb/ft ³	32.9

METHODSTrue & Apparent Specific Gravity: ASTM D 167; Porosity: Calculated Value
Density: ASTM D 291Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

February 19, 1999

PLEASE ADDRESS ALL CORRESPONDENCE TO:

16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060INLAND STEEL COMPANY
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill AmbreySample identification by
CT&E Co.Kind of sample
reported to us Furnace Coke

Sample ID: Mitsui Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled February 5, 1999

Release No. XXX

Date received February 5, 1999

P.O. No. 6-J-8802

Analysis Report No. 71-85160

Page 2 of 2

SIEVE ANALYSIS

<u>Passing</u>	<u>Retained on</u>	<u>% Weight</u>	<u>CUMULATIVE RESULTS</u>	
			<u>% Retained</u>	<u>% Passing</u>
-----	4" Sq	0.00	0.00	100.00
4" Sq	3" Sq	2.43	2.43	97.57
3" Sq	2" Sq	23.73	26.16	73.84
2" Sq	1" Sq	67.38	93.54	6.46
1" Sq	0	6.46	100.00	0.00

METHOD

Sieve Analysis: ASTM D 4749

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.*Joseph B. Fouser*
Manager, South Holland Laboratory

COMMERCIAL TESTING & ENGINEERING CO.

ISP0086

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306



SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

February 19, 1999

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

INLAND STEEL COMPANY
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill Ambrey

Sample identification by
CT&E Co.

Kind of sample
reported to us Furnace Coke

Sample ID: Shenango Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled February 5, 1999

Release No. XXX
P.O. No. 6-J-8802

Date received February 5, 1999

Analysis Report No. 71-85159

Page 1 of 2

Porosity	52.17
Apparent Specific Gravity	0.88
True Specific Gravity	1.84
Bulk Density lb/ft ³	32.5

METHODS

True & Apparent Specific Gravity: ASTM D 167; Porosity: Calculated Value
Density: ASTM D 291

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Joseph B. Ambrey
Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

February 19, 1999

PLEASE ADDRESS ALL CORRESPONDENCE TO:

16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473

TEL: (708) 331-2900

FAX: (708) 333-3060

INLAND STEEL COMPANY
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill AmbreySample identification by
CT&E Co.Kind of sample
reported to us Furnace Coke

Sample ID: Shenango Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled February 5, 1999

Release No. XXX

Date received February 5, 1999

P.O. No. 6-J-8802

Analysis Report No. 71-85159

Page 2 of 2

SIEVE ANALYSIS

<u>Passing</u>	<u>Retained on</u>	<u>% Weight</u>	<u>CUMULATIVE RESULTS</u>	
			<u>% Retained</u>	<u>% Passing</u>
-----	4" Sq	0.00	0.00	100.00
4" Sq	3" Sq	1.06	1.06	98.94
3" Sq	2" Sq	23.23	24.29	75.71
2" Sq	1" Sq	62.47	86.76	13.24
1" Sq	0	13.24	100.00	0.00

METHOD

Sieve Analysis: ASTM D 4749

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.*Joseph B. Ambrey*

Manager, South Holland Laboratory





COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

February 19, 1999

INLAND STEEL COMPANY
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill Ambrey

Sample identification by
CT&E Co.

Kind of sample
reported to us Furnace Coke

Sample ID: USX Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled February 5, 1999

Release No. XXX

Date received February 5, 1999

P.O. No. 6-J-8802

Analysis Report No. 71-85161

Page 1 of 2

Porosity	50.00
Apparent Specific Gravity	0.90
True Specific Gravity	1.80
Bulk Density lb/ft ³	34.3

METHODS

True & Apparent Specific Gravity: ASTM D 167; Porosity: Calculated Value
Density: ASTM D 291

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Joseph B. Foushee
Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:

16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

February 19, 1999

INLAND STEEL COMPANY
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill AmbreySample identification by
CT&E Co.Kind of sample
reported to us Furnace Coke

Sample ID: USX Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled February 5, 1999

Release No. XXX

Date received February 5, 1999

P.O. No. 6-J-8802

Analysis Report No. 71-85161

Page 2 of 2

SIEVE ANALYSIS

<u>Passing</u>	<u>Retained on</u>	<u>% Weight</u>	<u>CUMULATIVE RESULTS</u>	
			<u>% Retained</u>	<u>% Passing</u>
-----	4" Sq	0.00	0.00	100.00
4" Sq	3" Sq	2.66	2.66	97.34
3" Sq	2" Sq	25.51	28.17	71.83
2" Sq	1" Sq	49.98	78.15	21.85
1" Sq	0	21.85	100.00	0.00

METHOD

Sieve Analysis: ASTM D 4749

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.*Joseph B. Ambrey*
Manager, South Holland Laboratory

COMMERCIAL TESTING & ENGINEERING CO.

ISP0086

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

March 8, 1999

ISPAT INLAND, INC.
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill Ambrey

Sample identification by
CT&E Co.

Kind of sample
reported to us Furnace Coke

Sample ID: USX Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled January 29, 1999

Date received January 29, 1999

P.O. No. 6-J-8802
REVISED SIEVE ANALYSIS 03/08/99

Analysis Report No. 71-84772

Page 1 of 2


Porosity	53.30
Apparent Specific Gravity	0.92
True Specific Gravity	1.97
Bulk Density lb/ft ³	33.0

METHODS

True & Apparent Specific Gravity: ASTM D 167; Porosity: Calculated Value
Density: ASTM D 291

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Joseph B. Fouser
Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

March 8, 1999

PLEASE ADDRESS ALL CORRESPONDENCE TO:

16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473

TEL: (708) 331-2900

FAX: (708) 333-3060

ISPAT INLAND, INC.
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill AmbreySample identification by
CT&E Co.Kind of sample
reported to us Furnace Coke

Sample ID: USX Coke

Sample taken at Inland Steel Company.

Sample taken by CT&E Co.

Date sampled January 29, 1999

Date received January 29, 1999

P.O. No. 6-J-8802

REVISED SIEVE ANALYSIS 03/08/99

Analysis Report No. 71-84772


Page 2 of 2

SIEVE ANALYSIS


<u>Passing</u>	<u>Retained on</u>	<u>% Weight</u>	<u>CUMULATIVE RESULTS</u>	
			<u>% Retained</u>	<u>% Passing</u>
-----	4" Sq	0.00	0.00	100.00
4" Sq	3" Sq	1.48	1.48	98.52
3" Sq	2" Sq	55.66	57.14	42.86
2" Sq	1" Sq	24.25	81.39	18.61
1" Sq	0	18.61	100.00	0.00

METHOD

Sieve Analysis: ASTM D 4749

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Manager, South Holland Laboratory



COMMERCIAL TESTING & ENGINEERING CO.

ISP0086

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

PLEASE ADDRESS ALL CORRESPONDENCE TO:

16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

March 8, 1999

ISPAT INLAND, INC.
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill AmbreySample identification by
CT&E Co.Kind of sample
reported to us Furnace Coke

Sample ID: USX Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Date sampled February 1, 1999

P.O. No. 6-J-8802

Date received February 2, 1999

REVISED SIEVE ANALYSIS 3/8/99


Analysis Report No. 71-84903

Page 1 of 2

Porosity 61.34

Apparent Specific Gravity 0.75

True Specific Gravity 1.95

Bulk Density lb/ft³ 31.3METHODSTrue & Apparent Specific Gravity: ASTM D 167; Porosity: Calculated Value
Density: ASTM D 291Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.
Manager, South Holland Laboratory



Appl. No. 09/846 829

Filed 05/01/2009

COMMERCIAL TESTING & ENGINEERING CO.

GENERAL OFFICES: 1919 SOUTH HIGHLAND AVE., SUITE 210-B, LOMBARD, ILLINOIS 60148 • TEL: 708-953-9300 FAX: 708-953-9306

EXHIBIT D

64 of 64

ISP0086

SINCE 1908

Member of the SGS Group (Société Générale de Surveillance)

March 8, 1999

PLEASE ADDRESS ALL CORRESPONDENCE TO:
16130 VAN DRUNEN RD.
SOUTH HOLLAND, IL 60473
TEL: (708) 331-2900
FAX: (708) 333-3060

ISPAT INLAND, INC.
3210 Watling Street
Mail Code 8161
East Chicago, IN 46312
Attn: Bill Ambrey

Sample identification by
CT&E Co.

Kind of sample
reported to us Furnace Coke

Sample taken at Inland Steel Company

Sample taken by CT&E Co.

Sample ID: USX Coke

Date sampled February 1, 1999

P.O. No. 6-J-8802

Date received February 2, 1999

REVISED SIEVE ANALYSIS 3/8/99

Analysis Report No. 71-84903

Page 2 of 2

SIEVE ANALYSIS


<u>Passing</u>	<u>Retained on</u>	<u>% Weight</u>	<u>CUMULATIVE RESULTS</u>	
			<u>% Retained</u>	<u>% Passing</u>
-----	4" Sq	0.00	0.00	100.00
4" Sq	3" Sq	2.21	2.21	97.79
3" Sq	2" Sq	34.26	36.47	63.53
2" Sq	1" Sq	56.07	92.54	7.46
1" Sq	0	7.46	100.00	0.00

METHOD

Sieve Analysis: ASTM D 4749

Respectfully submitted,
COMMERCIAL TESTING & ENGINEERING CO.

Joseph B. Hrusch
Manager, South Holland Laboratory



OVER 40 BRANCH LABORATORIES STRATEGICALLY LOCATED IN PRINCIPAL COAL MINING AREAS, TIDEWATER AND GREAT LAKES PORTS, AND RIVER LOADING FACILITIES

165/071/95
inal Watermarked For Your Protection

TERMS AND CONDITIONS ON REVERSE

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record.**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.